



Material: Eggshell ceramic w/sodium alginate

Drying time: +48 hours

Texture: rigid, a little rough, easy to break and cracks when drying.

Observations: The mixture results in a type of dough/clay, it is easy to manipulate by hand, but not so much for using it in a mold, it may not capture the details of it.



Material: Eggshell ceramic w/gelatin

Drying time: 5 hours

Texture: rigid, rough, hard to break.

Observations: It dries almost instantly, which makes it difficult to mold, you have to pour it quickly into a mold before it solidifies.



Material: Eggshell ceramic w/xanthan gum

Drying time: 48 hours

Texture: rigid, rough, easy to break.

Observations: After preparing it, it is the most liquid mixture and therefore the easiest to pour into a mold and adapt to it, you can also experiment with extruding the mixture with a syringe.